

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 1 421 918 A1**

(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
26.05.2004 Bulletin 2004/22

(21) Application number: **03257295.0**

(22) Date of filing: **19.11.2003**

(51) Int Cl.7: **A61F 2/30, A61F 2/34,
A61F 2/38, A61L 27/04,
A61L 27/06, A61L 27/10,
A61L 27/30, B29C 43/20,
B29C 45/16**

(84) Designated Contracting States:
**AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IT LI LU MC NL PT RO SE SI SK TR**
Designated Extension States:
AL LT LV MK

(30) Priority: **19.11.2002 US 299435**

(71) Applicant: **Zimmer Technology, Inc.
Chicago, Illinois 60606 (US)**

(72) Inventors:
• **Charlebois, Steven J.
Warsaw, IN 46580 (US)**

• **Hawkins, Michael
Columbia City, IN 46725 (US)**
• **Swarts, Dale
Warsaw, IN 46582 (US)**
• **Blanchard, Cheryl
Warsaw, IN 46580 (US)**

(74) Representative: **Mays, Julie
Barker Brettell,
10-12 Priests Bridge
London SW15 5JE (GB)**

(54) **Prosthetic device and method of making the same**

(57) A method of making a non-modular prosthetic device for a joint arthroplasty. The method comprises molding a polymer interlayer (140) between a porous

metal structure (120) and a polymer insert (160), wherein the insert (160) generally comprises conventional or cross-linked ultra high molecular weight polyethylene ("UHMWPE").




FIG. 1

Description

BACKGROUND

1. Field of the Invention

[0001] The present invention is related generally to prosthetic orthopedic implants, particularly to joint components such as for use with knees, hips, shoulders, elbows, toes, fingers, wrists, ankles, spinal discs and the like. More specifically, the present invention relates to a method of making a non-modular prosthetic joint component having a polymer, ceramic, or metal bearing component bonded to a polymer, ceramic, or metallic substrate having at least one porous surface.

2. Description of the Related Art

[0002] Orthopedic implant devices known to those of skill in the art often comprise a backing component and bearing component attached thereto. Furthermore, it is often desirable for the metal backing component to comprise a porous structure or surface suitable for bone ingrowth after the prosthetic device is implanted. For example, a typical prosthetic acetabular cup comprises a hemispherical metal backing having a porous convex exterior and a solid concave interior. A similarly hemispherical, but smaller, polymer bearing surface is inserted into to the concave interior of the backing. In another example, a typical tibial component for use during a knee arthroplasty comprises metal tibial plateau having a porous bone contacting surface and a polymer bearing component attached to an opposing surface.

[0003] In many instances, prosthetic joint devices are modular. A modular device comprises a backing component, generally comprising a biocompatible metal having a porous structure or surface, and a separate bearing surface component, generally comprising a polymer. For example, a modular acetabular cup comprises a metal backing component and a polymer bearing surface fixedly inserted therein. Such fixation may be achieved via any of one or more of a variety of known mechanical means, such as snap fitting the components, press fitting the components, threadably connecting the components, using a locking ring, etc.

[0004] Those of skill in the art recognized that these additional mechanical retaining means could be avoided by using non-modular ("monoblock") joint components. Monoblock joint components comprise a metal backing such as a metal acetabular shell or a metal tibial plateau with the bearing surface integrally attached thereto. Unlike a modular component, the bearing surface of a monoblock is integral with the bearing component and need not be mechanically attached to the metal backing of an implant during an intraoperative step. There are several monoblock prosthetic devices presently available. These devices are generally produced by directly compression molding a thermoplastic poly-

mer bearing component onto a backing component. However, this method of producing monoblock devices has disadvantages.

[0005] More recently, the bearing components of traditional monoblock prosthetic devices often comprise cross-linked ultra high molecular weight polyethylene ("UHMWPE"). Cross linking can be accomplished chemically, but it is usually accomplished via gamma or electron beam irradiation after the monoblock device is assembled. A problem with this process is that the metal component of the monoblock device can shield the bearing component from the electron beam radiation used to initiate cross linking, thereby making cross linking of the bearing component more difficult and time consuming or possibly having areas within the polymer remaining uncrosslinked.

[0006] Another problem with monoblock processes known in the art is that such processes do not accommodate using non moldable materials such as metals or ceramics for the bearing surface, as the same cannot be compression or injection molded onto a backing component.

[0007] Thus, a need exists for a method of making a monoblock orthopedic joint device, wherein the polymer component can be cross-linked separately from the backing component and subsequently connected to thereto to form a monoblock device.

[0008] A still further need exists for a method of making a monoblock orthopedic joint utilizing a metal, ceramic or other non-flowable material for the bearing surface.

SUMMARY

[0009] The present invention comprises a novel method of making a monoblock prosthetic joint device having a polymer, metal, or ceramic bearing component fixedly attached to a porous metal component or a metal component. In such devices, the metal component is generally in communication or contact with an adjacent bone. The bearing surface (or articular surface) is generally in movable contact with another bone or an articular surface from an adjacent implant.

[0010] An advantage of the present invention is that a cross-linked polymer component may be attached to a metal component rather than attaching a non-cross-linked polymer and subsequently irradiating the same to create cross-links as the metal component may make such subsequent irradiation difficult.

[0011] Another advantage of the present invention is that the bearing surface may comprise a variety of materials, such as, thermoplastics, thermosets, metals, and ceramics, yet still be bonded the porous metal component.

[0012] These and other advantages and features of the present invention will be apparent to those skilled in the art upon review of the appended claims and drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

[0013] The above-mentioned and other features and objects of this invention, and the manner of obtaining them, will become more apparent and the invention itself will be better understood by reference to the following description of an embodiment of the invention taken in conjunction with the accompanying drawings, wherein:

FIG. 1 is a side cross-sectional view of a prosthetic acetabular cup according to the present invention.

FIG. 2 is a side cross-sectional view of prosthetic knee tibial component according to the present invention.

FIG. 3 is a diagrammatic view of a first embodiment of the present invention.

FIG. 4 is a front view of an interface according to the present invention.

FIG. 5 is a front view of an interface according to an alternative embodiment of the present invention.

FIG. 6 is a diagrammatic view of a second embodiment of the present invention.

[0014] Corresponding reference characters indicate corresponding parts throughout the several views. Although the drawings represent an exemplary embodiment of the present invention, the drawings are not necessarily to scale and certain features may be exaggerated to better illustrate and explaining the invention. The exemplification set out herein illustrates an exemplary embodiment of the invention only.

DETAILED DESCRIPTION

[0015] The present invention comprises a method of making a monoblock prosthetic device, having a porous metal component. FIGS. 1 and 2 show exemplary devices that can be made using the present method, including an acetabular cup for a hip prosthesis and a tibial plateau for a knee prosthesis. It will be appreciated by those of skill in the art that other prosthetic devices comprising a metal component and bearing component, such as, glenoid components for shoulder prostheses and the like could also be made by the present method.

[0016] Referring now to FIG. 3, there is shown a diagrammatical view of a first embodiment 300 of the present method. The method comprises the steps of: providing metal backing component 120 of desired shape; providing a bearing component 160 of desired shape, said component having a plurality of grooves 165 disposed thereon; placing metal component 120 and bearing component 160 into an injection molding device, such that a desired gap exists between bearing component 160 and porous metal component 120; and injection molding a polymer interlayer 140 between porous metal component 120 and bearing component 160, such that polymer interlayer 140 is in communication with the porous structure of metal component 120 and

grooves 165 of bearing component 160.

[0017] As used herein, the terms backing component 120, polymer interlayer 140, and bearing component 160, shall apply to such components generically without regard to a particular shape or prosthetic implant application. For example, the term bearing component 160 has equal application to the meniscus component of a knee prosthesis and to the articular surface of a prosthetic acetabular cup.

[0018] Referring again to FIG. 3, there is shown step 310 of method 300 comprising providing metal backing component 120. Metal backing component 120 comprises a textured surface 121 to which polymer interlayer 140 can attach. Preferably, metal backing 120 and surface 121 are entirely porous or surface 121 is porous and attached to metal backing 120 by means known commonly in the art. Alternatively, surface 121 of metal backing component 120 comprises a knurled surface, a roughened surface, or a grooved surface such that a mechanical bond can be created between interlayer 140 and surface 121. Metal component 120 comprises a biocompatible metal material selected from the group consisting of tantalum, titanium, cobalt chrome, and stainless steel. Metal backing component 120 is sufficiently porous to allow a polymer interlayer 140 to interdigitate therein (as shown in FIG. 6) during the molding process, described subsequently herein. Preferably, metal component 120 comprises a tantalum porous metal or a tantalum porous metal surface. An example of a suitable tantalum porous metal is disclosed in U.S. Pat. No. 5,282,861, entitled *Open Cell Tantalum Structures for Cancellous Bone Implants and Cell and Tissue Receptors*, issued on Feb. 1, 1994 to Richard B. Kaplan and assigned to Ultramet of Pomona, CA, the disclosure of which is hereby incorporated by reference herein. Those of skill in the art will recognize that any biocompatible material having a surface of sufficient porosity and suitable mechanical properties to avoid being adversely affected by the present method can be used in the present invention. Some exemplary biocompatible materials include: stainless steel, cobalt chrome alloy, titanium, and titanium alloys.

[0019] Metal backing component 120 further comprises a shape appropriate for use in a particular orthopedic implant. For example, metal backing component 120 of step 310 could be shaped into a hemispherical shell for use in an acetabular cup implant as shown in FIG. 1. Alternatively, metal component 120 could be shaped into a plate for use as a tibial plateau, as shown in FIG. 2.

[0020] Referring still to FIG. 3, the method of the present invention further comprises step 320, wherein bearing component 160 of desired shape is provided. Bearing component 160 comprises a material selected from the group consisting of thermosets, thermoplastics, metals and ceramics, including, for example, polyurethane, polyethylene, and cross-linked polyethylene, titanium alloy, cobalt alloy, alumina, and zirconia. Bearing component 160 is shaped in a manner suitable for

a particular orthopedic implant. For example, as shown in FIG. 1, bearing component 160 comprises a hemispherical shape that can be disposed within the concave interior of an acetabular cup shell. Alternatively, as shown in FIG. 2, bearing component 160 may, by way of example and not limitation, comprise a shape suitable for a prosthetic knee meniscus.

[0021] Referring now to FIG. 4, there is shown bearing surface 160. Bearing surface 160 comprises grooves 165 to which polymer interlayer 140 can attach or "interdigitate." In a first embodiment of the present invention, grooves 165 are disposed around a portion of the exterior of bearing component 160 such that metal component 120 may be at least partially disposed therearound as shown in FIG. 6, and described in more detail below. In other embodiments of the invention (FIG. 5) bearing component 160 may comprise in place of grooves, a textured surface, a knurled surface, or a surface having a plurality of machined or molded indentations, as shown in FIG. 5.

[0022] Referring again to FIG. 3, there is shown step 330 of method 300. Step 330 comprises placing porous backing component 120 and bearing component 160 into an injection molding device. Any injection molding device capable of transporting and curing a chosen polymer material is satisfactory. The molding device should also be capable of accommodating metal backing component 120 and bearing component 160 in its mold. Components 120 and 160 should be placed in the mold such that the at least one porous surface of metal component 120 faces a textured surface of bearing component 160. A gap of desired distance should exist within the mold between components 120 and 160.

[0023] Referring still to FIG. 3, there is shown step 340 of method 300, wherein a polymer interlayer 140 is thereafter injection molded into the gap. Interlayer 140 comprises any biocompatible thermoplastic polymer, including, for example, polyethylene, PEEK (a trademark polyketone of the Vitrex company); other polyketones; and polyurethane. During the injection molding process, interlayer 140 flows at least partially around the interlock means of bearing component 160 and at least partially into the porous surface of metal component 120. Upon curing, interlayer 140 mechanically locks itself to bearing component 160 and metal component 120, as illustrated in FIG. 6. Thus, a bond is created between components 120 and 160 via interlayer 140. Those of skill in the art will appreciate that it is preferable for interlayer 140 to comprise a polymer that is miscible with the material used for bearing component 160. For example, a polyethylene interlayer 140 should be used with cross-linked ultrahigh molecular weight polyethylene bearing components 160 because such interlayer 140 will provide an adhesive as well as a mechanical bond between interlayer 140 and bearing component 160.

[0024] Turning now to FIG. 6, there is shown another embodiment of the present invention, method 600. Method 600 comprises the steps of: providing a porous

backing component 120 of desired shape; providing a bearing component 160 of desired shape, said component having polymer interlock means 165; placing the porous backing structure and the bearing component into a compression molding device, such that a desired gap exists between the bearing component and the porous structure; placing a layer of polymer resin in the gap between the porous surface of the backing component and the textured surface of the bearing component, such that the polymer layer is in communication with the porous structure and the textured surface of the bearing component, thereby forming an assembly; and subjecting the assembly to a compression molding cycle such that the polymer layer forms a solid interlayer, wherein the interlayer bonds the porous structure and the bearing component.

[0025] The steps of method 600 are as described above with regard to other embodiments of the present invention except for steps 640 and 650 described subsequently herein. Step 640 of method 500 comprises placing a polymer resin in a compression molding device adjacent to and in communication with a porous surface of backing component 120 and in communication with a textured surface of bearing component 160. This polymer resin will act as polymer interlayer 140. Those of skill in the art will appreciate that interlayer 140 may be provided in any usable form, including for example flakes or powder. Polymer interlayer 140 may, as disclosed previously herein, comprise any biocompatible thermoplastic polymer, including PEEK (a trademarked polyketone of the Vitrex company); polyethylene, UHMWPE, polyurethane, and the like. The combination of interlayer 140 in communication with metal component 120 and bearing component 160 is referred to herein as assembly 180.

[0026] Referring still to FIG. 6, there is shown step 650 of method 600 in which assembly 180 is subjected to a compression molding cycle such that interlayer 140 flows into the porous surface of metal component 120 and around interlock means 165 of bearing component 160, respectively. The compression molding cycle generally comprises utilizing a pressure from about 100 psi to about 600 psi for a time of about 1 to about 6 hours; and a temperature from about 150°C to about 200°C. Interlayer 140 mechanically secures itself into these surfaces as illustrated in FIGS. 4-5. After molding is complete, a near finished orthopedic implant has been produced.

[0027] In prior art methods of creating a monoblock prosthetic device, non-cross-linked material was molded directly to the porous surface of the metal component. In order to produce an implant having a cross-linked polymer bearing surface material the cross-linking is performed after the implant is assembled by irradiating the part. However, it is difficult to achieve uniform cross-link density using such practices because the metal component disrupts electron beam or gamma radiation that is generally used to initiate cross-linking in

a polymer. An advantage, therefore, of the present method is that a bearing component comprising a cross-linked material may be bonded to a metal component without having to subsequently irradiate the part to cross-link the bearing component.

[0028] Another advantage of the present method is that it provides a means by which non-flowable materials may be used to form the bearing surface in that the bond between components 120 and 160 exists via interlayer 140. For example, the present method can bond a ceramic bearing component 160 having at least one textured or porous surface with a porous metal component 120.

[0029] It will be appreciated by those skilled in the art that the foregoing is a description of a preferred embodiment of the present invention and that variations in design and construction may be made to the preferred embodiment without departing from the scope of the invention as defined by the appended claims.

Claims

1. A prosthetic implant comprising: a bearing component, the bearing component having an interlock means disposed on the exterior surface thereof; a backing component, the backing component having a textured surface; and a polymer interlayer disposed between the interlock means and the textured surface thereby connecting the bearing component to the backing component, wherein the bearing component and the interlayer are not made of the same material.
2. The apparatus of claim 1, wherein the textured surface of the backing component is selected from the group consisting of a knurled surface, a roughened surface, a porous surface, and an adhesive surface.
3. The apparatus of claim 1, wherein the bearing component comprises a material selected from the group consisting of polymers, UHMWPE, polyethylene, polyurethane, PEEK, metals, cobalt chrome, titanium, tantalum, ceramics, alumina, and zirconia.
4. The apparatus of claim 1, wherein the backing component comprises a material selected from the group consisting of tantalum, titanium, titanium alloy, stainless steel, cobalt chrome alloy, niobium, polymers, UHMWPE, polyethylene, polyurethane, PEEK, metals, cobalt chrome, titanium, tantalum, ceramics, alumina, and zirconia.
5. The apparatus of claim 1, wherein the polymer interlayer comprises a material selected from the group consisting of polyethylene, polyurethane, PEEK, and UHMWPE.
6. The apparatus of claim 1, wherein the interlock means is selected from the group consisting of a plurality of grooves disposed on the exterior of the bearing component, a knurled surface on the exterior of the bearing component, and an indented surface on the exterior of the bearing component.
7. A method of making a monoblock prosthetic device, the method comprising:
 - providing a backing component of desired shape having at least one porous surface,
 - providing a bearing component of desired shape, said component having a polymer interlock means;
 - molding a polymer interlayer between the at least one porous surface and the interlock means of the bearing component, such that the polymer layer is in communication with the at least one porous surface and the interlock means of the bearing component such that the interlayer affixes the backing component to the bearing component.
8. The method of claim 7, wherein the bearing component comprises a material selected from the group consisting of polymers, UHMWPE, polyethylene, polyurethane, PEEK, metals, cobalt chrome, titanium, tantalum, ceramics, alumina, and zirconia.
9. The method of claim 7, wherein the backing component comprises a material selected from the group consisting of tantalum, titanium, titanium alloy, stainless steel, cobalt chrome alloy, niobium, polymers, UHMWPE, polyethylene, polyurethane, PEEK, metals, cobalt chrome, titanium, tantalum, ceramics, alumina, and zirconia.
10. The method of claim 7, wherein the polymer interlayer comprises a material selected from the group consisting of polyethylene, polyurethane, PEEK, and UHMWPE.
11. The method of claim 7, wherein the interlock means is selected from the group consisting of a plurality of grooves disposed on the exterior of the bearing component, a knurled surface on the exterior of the bearing component, and an indented surface on the exterior of the bearing component.




FIG.1




FIG.2




FIG. 3





FIG. 6




FIG.5



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 03 25 7295

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	GB 2 126 096 A (MCKEE) 21 March 1984 (1984-03-21)	1,3-6	A61F2/30 A61F2/34
Y	* page 1, right-hand column, line 91 - line 122 * * page 2, left-hand column, line 22 - line 52; claim 6; figure 3 *	2,7-11	A61F2/38 A61L27/04 A61L27/06 A61L27/10 A61L27/30
Y	EP 0 648 478 A (BRISTOL-MYERS SQUIBB COMPANY) 19 April 1995 (1995-04-19)	2	B29C43/20 B29C45/16
A	* column 4, line 22 - column 5, line 25; figures 3-5 *	1,3-6	
Y	EP 0 803 234 A (BIOMET LIMITED) 29 October 1997 (1997-10-29)	7-11	
A	* column 5, line 9 - line 14 * * column 6, line 19 - line 30; claim 4; figure 5 *	1,3-5	
A	WO 01 24739 A (EXACTECH) 12 April 2001 (2001-04-12)	1,3-11	
	* the whole document *		TECHNICAL FIELDS SEARCHED (Int.Cl.7)
A	EP 0 681 845 A (BRISTOL-MYERS SQUIBB COMPANY) 15 November 1995 (1995-11-15)		A61F B29C
A	EP 0 554 214 A (SULZER MEDIZINALTECHNIK) 4 August 1993 (1993-08-04)		
A	US 6 087 553 A (COHEN) 11 July 2000 (2000-07-11)		
A	DE 297 04 605 U (DR. HELBIG) 7 May 1997 (1997-05-07)		
A	EP 0 343 511 A (WEIGEL) 29 November 1989 (1989-11-29)		
	-/--		
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 18 March 2004	Examiner Klein, C
CATEGORY OF CITED DOCUMENTS		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document			

EPO FORM 1503 03.92 (P04C01)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 03 25 7295

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	US 5 702 649 A (TAYLOR) 30 December 1997 (1997-12-30) ---		
D,A	US 5 282 861 A (KAPLAN) 1 February 1994 (1994-02-01) -----		
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 18 March 2004	Examiner Klein, C
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

EPO FORM 1503 (03.82) (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 03 25 7295

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

18-03-2004

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
GB 2126096	A	21-03-1984	NONE		

EP 648478	A	19-04-1995	CA	2133718 A1	19-04-1995
			EP	0648478 A2	19-04-1995
			JP	7171174 A	11-07-1995

EP 803234	A	29-10-1997	EP	0803234 A1	29-10-1997
			US	5879404 A	09-03-1999

WO 0124739	A	12-04-2001	US	2001037156 A1	01-11-2001
			AU	7996700 A	10-05-2001
			WO	0124739 A2	12-04-2001

EP 681845	A	15-11-1995	CN	1114225 A	03-01-1996
			DE	69512304 D1	28-10-1999
			DE	69512304 T2	23-03-2000
			EP	0681845 A2	15-11-1995
			ES	2138699 T3	16-01-2000
			JP	8019559 A	23-01-1996
			US	5645594 A	08-07-1997

EP 554214	A	04-08-1993	AT	149329 T	15-03-1997
			DE	59305553 D1	10-04-1997
			EP	0554214 A1	04-08-1993
			EP	0726066 A2	14-08-1996
			ES	2098016 T3	16-04-1997

US 6087553	A	11-07-2000	NONE		

DE 29704605	U	07-05-1997	DE	29704605 U1	07-05-1997
			AT	220311 T	15-07-2002
			DE	59707675 D1	14-08-2002
			EP	0808615 A2	26-11-1997
			US	6451139 B1	17-09-2002
			US	6113634 A	05-09-2000

EP 343511	A	29-11-1989	DE	3817525 A1	07-12-1989
			AT	102866 T	15-04-1994
			DE	58907201 D1	21-04-1994
			EP	0343511 A2	29-11-1989
			FI	892490 A	25-11-1989

US 5702649	A	30-12-1997	JP	3021347 B2	15-03-2000
			JP	8271708 A	18-10-1996

US 5282861	A	01-02-1994	DE	69328843 D1	20-07-2000

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

